
FAVINI

e-mail: rossano@favini.com
Website: www.favini.com

LAGUNA



PRODUCT DESCRIPTION

Laguna has a timeless elegance, thanks to its traditional parchment finish. It is available in 10 soft shades and is perfect for applications such as greetings cards, invitations, menus, certificates and product guarantees - in fact anything that needs some classic style.

TECHNICAL DATA

	METHOD		+/-	90 g/m²	180 g/m²	300 g/m²
BASIC WEIGHT	ISO 536	g/m²	5%	90	180	300
CALIPER	ISO 534	µm	5%	128	248	390
BULK	ISO 534	cm²/g	-	1,42	1,38	1,30
OPACITY	ISO 2471	%	>	87	-	-
MOISTURE CONTENT	ISO 287	%	1,0	6,0	6,0	6,0

Special makings are available upon request.

ECF ELEMENTAL CHLORINE FREE
FREE ACID
94/62 EC HEAVY METAL COMPLIANT
25/40 EN PPWR COMPLIANT
21 PAP
22 PAP
FSC www.fsc.org FSC® C001810 The mark of responsible forestry

PRINTING AND FINISHING RECCOMENDATIONS

INKS	To ensure good drying, use semi-fresh inks, preferably new and undiluted.
BLANKETS	For a good graphic impression, use compressible blankets suitable for offset printing machines in any conditions.
DRYING TIME	After printing, make small sheet pallets and allow 24 hours drying time.
SCREENS	For the offset printing process a screen value of 135-150 lpi is recommended. For dry offset printing this can be slightly higher, for example 200 lpi. For heavier graphic elements and higher densities, sufficient powder should be applied.
FINISHING	Prescoring is recommended for board weights and when folding against the grain direction.
VARNISHING	Preferably silkscreen UV.
PRINTABILITY AND RUNNABILITY	Every method of printing, embossing, punching, die cutting, creasing, laminating and UV varnishing is possible.
NOTE	Due to its hygroscopic nature, paper can show curl issues if not conditioned properly. To avoid any issue, we recommend to store the paper closed in its original wrap inside the printing area for at least 24-48 hours. After this conditioning time, the wrapping can be open and the paper can be utilized.

> Please contact our technical department for further suggestions.

MILL ACCREDITATION I Rossano Veneto VI - Italy

CORPORATE QUALITY MANAGEMENT STANDARD I UNI EN ISO 9001

ENVIRONMENTAL MANAGEMENT STANDARD I UNI EN ISO 14001

OCCUPATIONAL HEALTH AND SAFETY MANAGEMENT STANDARD I UNI EN ISO 45001

ECO-MANAGEMENT AND AUDIT SCHEME CE 1221/2009 I EMAS

We care about the environment: www.favini.com/en/sustainability