
FAVINI

e-mail: rossano@favini.com
Website: www.favini.com

PRISMA METALLIC



PRODUCT DESCRIPTION

Prisma is a timeless Favini classic. Its refined felt marking, with a delicate hammered effect, enhances creativity, printed communications, and high-quality packaging.
The range includes a two-sided version, designed for the graphic design world, and a one-sided line, ideal for education and hobby use, available in a wide colour palette.

Our latest addition to the range are four new fresh and versatile shades - Ecru, Powder, Sage, and Dusky Blue. The Digital and Metallic versions complete the range.

TECHNICAL DATA

	METHOD		+/-	260 g/m²
BASIC WEIGHT	ISO 536	g/m²	5%	260
CALIPER	ISO 534	µm	5%	380
BULK	ISO 534	cm²/g	-	1,5
L&W STIFFNESS MD/CD 15°/50MM	ISO 2493	mN	>	145/72
MOISTURE CONTENT	ISO 287	%	1,0	6,0

Special makings are available upon request.

ECF ELEMENTAL CHLORINE FREE
FREE ACID
REACH COMPLIANT
21 PAP
FSC www.fsc.org FSC™ C001810 The mark of responsible forestry

PRINTING AND FINISHING RECCOMENDATIONS

INKS	Good quality oxidizing inks. The drying process can be slightly accelerated by adding extra desiccant. Otherwise print with UV inks.
BLANKETS	For a good graphic impression, use compressible blankets.
SCREENS	For the offset printing process a screen value of 150-163 lpi is recommended. For heavier graphic elements and higher densities, sufficient powder should be applied.
DRYING TIME	Make small sheet pallets and allow at least 24 hours drying time after printing.
FINISHING	Prescoring is recommended for board weights and when folding against the grain direction.
PRINTABILITY AND RUNNABILITY	Every method of printing, embossing, punching, die cutting, creasing, laminating and UV varnishing is possible.
NOTE	Due to its hydroscopic nature, paper can show curl issues if not conditioned properly. To avoid any issue, we recommend to store the paper closed in its original wrap inside the printing area for at least 24-48 hours. After this conditioning time, the wrapping can be open and the paper can be utilized.

> Please contact our technical department for further suggestions.

MILL ACCREDITATION I Rossano Veneto VI - Italy

CORPORATE QUALITY MANAGEMENT STANDARD I UNI EN ISO 9001

ENVIRONMENTAL MANAGEMENT STANDARD I UNI EN ISO 14001

OCCUPATIONAL HEALTH AND SAFETY MANAGEMENT STANDARD I UNI EN ISO 45001

ECO-MANAGEMENT AND AUDIT SCHEME CE 1221/2009 I EMAS

We care about the environment: www.favini.com/en/sustainability