


## BIANCOFLASH IVORY

### PRODUCT DESCRIPTION

Warm ivory shade paper and boards made with FSC™ pulps from certified and controlled sources. Smooth touch, elegant shade. Available in 7 grammages, 1 size and matching envelopes.



TECHNICAL DATA	METHOD		+/-	85 g/m <sup>2</sup>	120 g/m <sup>2</sup>	170 g/m <sup>2</sup>	200 g/m <sup>2</sup>	250 g/m <sup>2</sup>	300 g/m <sup>2</sup>	350 g/m <sup>2</sup>
BASIC WEIGHT	ISO 536	g/m <sup>2</sup>	5%	85	120	170	200	250	300	350
CALIPER	ISO 534	µm	5%	91	128	183	214	266	322	375
BULK	ISO 534	cm <sup>2</sup> /g	-	1,07	1,07	1,07	1,07	1,07	1,07	1,07
ROUGHNESS (BENDTSEN)	ISO 8791-2	ml/min	30	90	90	90	90	90	90	90
OPACITY	ISO 2471	%	>	88	92	-	-	-	-	-
MOISTURE CONTENT	ISO 287	%	1,0	5,5	6	6,5	6,5	6,5	6,5	6,5

Special makings are available upon request.



RECYCLABLE



BIODEGRADABLE



ELEMENTAL  
CHLORINE  
FREE



ACID



SAFETY TOYS



REACH  
COMPLIANCE



HEAVY METAL  
COMPLIANT



PAP



PAP



FSC® C001810  
The mark of  
responsible forestry

## PRINTING AND FINISHING RECCOMENDATIONS

INKS	To ensure good drying, Biancoflash Ivory papers should be printed with good quality semi-fresh inks. The drying process can be slightly accelerated by adding extra desiccant.
BLANKETS	For a good graphic impression, use compressible blankets.
SCREENS	For the offset printing process a screen value of 150 lpi is recommended. For dry offset printing this can be slightly higher, for example 200 lpi. For heavier graphic elements and higher densities, sufficient powder should be applied.
DRYING TIME	Allow 24 hours drying time after printing.
FINISHING	Prescoring is recommended for board weights and when folding against the grain direction.
PRINTABILITY AND RUNNABILITY	Every method of printing, embossing, punching, die cutting, creasing, laminating and UV varnishing is possible.
NOTE	Due to its hygroscopic nature, paper can show curl issues if not conditioned properly. To avoid any issue, we recommend to store the paper closed in its original wrap inside the printing area for at least 24-48 hours. After this conditioning time, the wrapping can be open and the paper can be utilized.

> Please contact our technical department for further suggestions.

## MILL ACCREDITATION | Rossano Veneto VI - Italy

CORPORATE QUALITY MANAGEMENT STANDARD | UNI EN ISO 9001

ENVIRONMENTAL MANAGEMENT STANDARD | UNI EN ISO 14001

OCCUPATIONAL HEALTH AND SAFETY MANAGEMENT STANDARD | UNI EN ISO 45001

ECO-MANAGEMENT AND AUDIT SCHEME CE 1221/2009 | EMAS

We care about the environment: [www.favini.com/en/sustainability](http://www.favini.com/en/sustainability)