
FAVINI

**e-mail:** rossano@favini.com
**Website:** www.favini.com

Technical Data Sheet | 18.11.2026

# CLASSY COVERS GLOSSY




## PRODUCT DESCRIPTION

Classy Covers Glossy is the perfect embossed covering for books, binders and folders.
It is pulp tinted. It may be used for a large number of packaging applications including shopping bags. The papers meet the highest standards of foldability and scuff resistance and have excellent light fastness. Available in 4 glossy colours.

## TECHNICAL DATA

| | METHOD | | +/- | 125 g/m² |
|---|---|---|---|---|
| BASIC WEIGHT | ISO 536 | g/m² | 5% | 125 |
| GLOSS 60° | TAPPI T480 | % | > | 4 |
| BREAKING LENGTH LONG | ISO 1924 | km | > | 5 |
| BREAKING LENGTH CROSS | ISO 1924 | km | > | 3 |
| STIFFNESS LONG (15°/15mm) | ISO 2493 | mN | > | 100 |
| STIFFNESS CROSS (15°/15mm) | ISO 2493 | mN | > | 40 |
| TEAR RESISTANCE LONG | ISO 1974 | mN | > | 700 |
| TEAR RESISTANCE CROSS | ISO 1974 | mN | > | 600 |
| MOISTURE CONTENT | ISO 287 | % | 1 | 6,0 |

*Special makings are available upon request.*

RECYCLABLE
ECF ELEMENTAL CHLORINE FREE PULP
FREE ACID
25/40 EN PPWR COMPLIANT

REFERS TO CLASSY COVERS GLOSSY BLACK
FREE CARBON BLACK

22 PAP

FSC www.fsc.org FSC® C001810 The mark of responsible forestry

FAVINI

**e-mail:** rossano@favini.com
**Website:** www.favini.com

Technical Data Sheet | 18.11.2026

## PRINTING AND FINISHING RECCOMENDATIONS

**INKS**
To ensure good drying, Classy Covers Glossy papers should be printed with oxidizing inks. The drying process can be slightly accelerated by adding extra desiccant. Always use anti-set off.

**PRINTING PRESSURE**
The embossing requires proper printing pressure settings.

**HOT FOIL STAMPING**
There are no precautions necessary when using conventional foil stamping techniques.

**THERMOGRAPHY, SILKSCREEN AND UV VARNISHING**
The product is suitable for these techniques.

**PRINTABILITY AND RUNNABILITY**
Classy Covers Glossy has excellent properties for these techniques: Cutting, Creasing, Folding, Blind Embossing and Die stamping.

**NOTE**
Due to its hygroscopic nature, paper can show curl issues if not conditioned properly. To avoid any issue, we recommend to store the paper closed in its original wrap inside the printing area for at least 24-48 hours. After this conditioning time, the wrapping can be open and the paper can be utilized.

*> Please contact our technical department for further suggestions.*

## ROSSANO VENETO MILL IS:

REACH COMPLIANT

## **MILL ACCREDITATION** | Rossano Veneto VI - Italy

**CORPORATE QUALITY MANAGEMENT STANDARD** | UNI EN ISO 9001

**ENVIRONMENTAL MANAGEMENT STANDARD** | UNI EN ISO 14001

**OCCUPATIONAL HEALTH AND SAFETY MANAGEMENT STANDARD** | UNI EN ISO 45001

**ECO-MANAGEMENT AND AUDIT SCHEME CE 1221/2009** | EMAS

**We care about the environment: www.favini.com/en/sustainability**